# **Product information**

# Silicone Sealing Compound, black



### **Description**

Black Silicone Sealing Compound is a heat-resistant, single-component sealant that vulcanizes under the influence of air humidity and cures to form a permanently elastic mass. Black Silicone Sealing Compound can be used to seal a wide variety of materials (e.g. metal, plastic, glass, porcelain, painted wood surfaces, etc.) in engines, transmissions, vehicles, containers, plants and heating facilities as well as in air conditioning systems.

## **Properties**

- adheres well to vertical surfaces
- resistant to stresses and vibrations
- outstanding thermal stability
- free of solvents, formaldehyde, CFCs, PCB, PCP
- permanently elastic
- enables a multifaceted range of applications
- outstanding chemical resistance

#### **Technical data**

Curing rate at 23 °C / 50 %  $\sim$  2,0 mm/24h rh

Density 0,95 - 1,28 g/cm $^3$ Tensile stress at 100 % ~ 0,60 N/mm $^2$ elongation DIN 52455

Base Silikon auf Oximbasis 7

Silicone with oxime basis

Operating temperature -65°C bis +260°C, range kurzfristig bis +315°C

Penetration after 5 185 +/- 30 1/10 mm seconds DIN 51579

Hardness, Shore A 40 +/- 5 DIN 53505

Processing temperature +5°C bis +40°C / +5°C to

+40°C

Skin formation time at 23 ~ 8 min °C/50 % relative humidity

Color / appearance je nach Spezifikation /

according to specification

Odor charakteristisch /

characteristic

Form pastös, flüssig / pastelike,

liquid

Viscosity at 40 °C >7 mm<sup>2</sup>/s

pH value 7

Shelf life in original sealed 24 Monate

container

#### Technical data

Shelf life in original sealed 24 Monate container

## Areas of application

Black Silicone Sealing Compound is exceptionally well-suited to sealing housings on engines, transmissions, differentials, end covers, oil pans, valve covers, water pumps, battery boxes, headlights and other lights, etc.

### **Application**

The surfaces to be sealed must be clean, dry and free of oil and grease. Remove cap and turn cartridge tip by 90°. Apply material evenly and immediately join parts without flash-off time. After applying, turn cartridge tip by 90° again and press cap onto nozzle.

Note: Insufficient adhesion on substrates such as PP, PE, Teflon and bitumen can be expected. This is why we recommend that you carry out an adhesion test prior to application.

#### Available pack sizes

80 ml Cartridge plastic 6177

D-GB-F-ARAB

80 ml Cartridge plastic 7639

RUS-UA

200 ml Can aerosol 6185

D-GB-F-I-E-NL-P

200 ml Can aerosol 2859

GB-DK-FIN-N-S

Our information is based on thorough research and may be considered reliable, although not legally binding.

Phone: +49 (0)731/1420-13 Fax: +49 (0)731/1420-82 e-mail: info@liqui-moly.de Service-hotline: 0800/8323230 Technical hotline: +49 (0)731/1420-871 www.liqui-moly.de